


GYTA



Characteristic of Optical Cable

- Min. bending radius for installation
Static: 10 x cable diameter
Dynamic: 20 x cable diameter
- Application temperature range
Operation: - 30°C ~ +70°C
Installation: -10°C ~ +60°C
Storage/transportation: - 40°C ~ +70°C

Cable Specification:

Loose tube construction, tubes jelly filled, elements (tubes and filler rods) laid up around metallic central strength member, polyester yarns used to bind the cable core, filling compound filled in the apertures of the cable core, then Al tape and PE outer sheath.

Cable structure and parameter

SN	Item	Unit	Value					
1	No. of fibers	count	12//24	36	48	72	120	144
2	No. of fibers per tube	count	6	6	12	12	12	12
3	No. of elements	count	5	6	5	6	10	12
4	Cable diameter(±5%)	mm	8.7	9.2	9.6	10.3	13.2	14.5
5	Cable weight(±10%)	kg/km	73	91	92	119	170	199
6	Short term tension	N	1500					
7	Short term crush	N/100mm	1000					

Fiber color code

1	2	3	4	5	6	7	8	9	10	11	12
Blue	Orange	Green	Brown	Gray	White	Red	Black	Yellow	Purple	Pink	Aqua
Color codes for loose tube & filler rod											
1	2	3	4	5	6	7	8	9	10	11	12
Blue	Orange	Green	Brown	Gray	White	Red	Black	Yellow	Purple	Pink	Aqua

Main mechanical & environmental performance test

Item	Test Method	Acceptance Condition
Tensile Strength IEC 60794-1-2-E1	- Load: Short term tension - Length of cable: about 50m - Load time: 1min	- Fiber strain $\leq 0.6\%$ - No fiber break and no sheath damage.
Crush Test IEC 60794-1-2-E3	- Load: Short term crush - Load time: 1min	- Loss change $\leq 0.1\text{dB}@1550\text{nm}$ - No fiber break and no sheath damage.

Characteristic of Optical Fiber

G652D fiber information

Mode field diameter (1310nm):	$9.2\mu\text{m}\pm 0.4\mu\text{m}$
Mode field diameter (1550nm):	$10.4\mu\text{m}\pm 0.8\mu\text{m}$
Cut off wavelength of cabled fiber (λ_{cc}):	$\leq 1260\text{nm}$
Attenuation at 1310nm:	$\leq 0.36\text{dB/km}$
Attenuation at 1550nm:	$\leq 0.22\text{dB/km}$
Bending loss at 1550nm (100 turns, 30mm radius):	$\leq 0.05\text{dB}$
Dispersion in the range 1288 to 1339nm:	$\leq 3.5\text{ps}/(\text{nm}\cdot\text{km})$
Dispersion at 1550nm:	$\leq 18\text{ps}/(\text{nm}\cdot\text{km})$
Dispersion slope at zero dispersion wavelength:	$\leq 0.092\text{ps}/(\text{nm}^2\cdot\text{km})$